

 **NEMO**

**COTTO CEMENTO**



# COTTO CEMENTO




# COTTO CEMENTO




# COTTO CEMENTO

PORCELAINED STONEWARE WITH MASS COLOURING


## SIZES



75,5x75,5 (30"x30") RET. T.



60x60 (24"x24") N AT.  
59,5x59,5 (24"x24") RET. T.



ESA GONO  
60x52 (24"x20") RET. T.



37,5x75,5 (15"x30") RET. T.



30x60 (12"x24") N AT.  
29,7x59,5 (12"x24") RET. T.



29,7x29,7 (12"x12") RET. T.

## COLOURS



Greige



Ghiaccio



Cenere



Grigio




Vintage only in  
24"x24"

## DECORS

Mosaico 2,2x2, 2 (0,87"x0,87")



## TRIMS




Battiscopa Naturale ?  
7,5x60 (3"x24") ?

Battiscopa Naturale Rett.  
7,5x59,5 (3"x24") ?

## DCOF = 0,51



75,5x75,5  
60x60  
59,5x59,5  
37,5x75,5  
Esagono



30x60  
29,7x59,5  
30x30 Mosaico Mix

# COTTO CEMENTO

GM

## GRES PORCELLANATO CON COLORAZIONE IN MASSA

PORCELAINED STONEWARE WITH MASS COLOURING

GRES CERAME AVEC PATE COLOREE

DURCHGEFÄRBTES FEINSTEINZEUG

GRES PORCELÁNICO CON COLORACIÓN EN MASA

ФАРФОРОВЫЙ КЕРАМОГРАНИТ, ОКРАШЕННЫЙ ПО ВСЕЙ ТОЛЩИНЕ

CE Bla GL

Gruppo di appartenenza secondo ISO 13006

Class - Groupe d'appartenance

Zugehörigkeitsgruppe - Grupo de pertenencia

Группа принадлежности

Simbologia Symbolics Symboles Symbole Simbologias Символы	Caratteristiche Features Caracteristiques Eigenschaften Caracteristicas Характеристика	Unità di misura Unit of measurement Unité de mesure Masseinheit Unidad de medida Единица измерения	Valore medio Saime Saime mean value Valeur moyenne Saime Durchschnitts-Werf-Saime Valor medio Saime Среднее значение Saime	Valore prescritto Fixed value Valeur prescrite Vorgeschriebener Wert Valor prescrito Требуемое значение	Metodo di prova Test method Méthode d'essai Prüfmethode Método de ensayo Метод испытания
	<b>Dimensione lati</b> Dimensions-Length and width - Dimensions-Longueur et largeur - Masse-Länge und Breite Dimensiones-Longitud y ancho - <b>Размеры сторон</b>	%	+/- 0,4	+/- 0,6 max	UNI EN ISO 10545-2
	<b>Rettilineità dei lati</b> Side straightness - Rectitude des arêtes Geractlinigkeit der Kanten - Rectilinedad de los lados <b>Прямолинейность сторон</b>	%	+/- 0,4	+/- 0,5 max	UNI EN ISO 10545-2
	<b>Ortogonalità degli spigoli</b> Corner squariness - Angularité Rechtwinkligkeit der Kanten - Ortogonalidad de las esquinas - <b>Ортогональность кромок</b>	%	+/- 0,4	+/- 0,6 max	UNI EN ISO 10545-2
	<b>Planarità</b> Flatness - Planéité Ebenfächigkeit - Planeidad <b>Плоскостность</b>	%	+/- 0,4	+/- 0,5 max	UNI EN ISO 10545-2
	<b>Spessore</b> Thickness - Epaisseur Dicke - Grosor - <b>Толщина</b>	%	+/- 5,0	+/- 5,0 max	UNI EN ISO 10545-2
	<b>Assorbimento d'acqua</b> Water absorption - Absorption d'eau Wasseraufnahme - Absorción de agua <b>Водопоглощение</b>	%	< 0,2	≤ 0,5	UNI EN ISO 10545-3
	<b>Sforzo di rottura</b> Breaking strength - Contrainte de rupture Bruchkraft - Esfuerzo de rotura <b>Разрушающее усилие</b>	N	> 1600	≥ 1300 se Spess. ≥ 7,5 ≥ 700 se Spess. ≤ 7,5	UNI EN ISO 10545-4
	<b>Modulo di rottura</b> Modulus of rupture - Coefficient de rupture Bruchmodul - Módulo de rotura <b>Модуль разрыва</b>	N/mm²	> 40	≥ 35	UNI EN ISO 10545-4
	<b>Dilatazione termica lineare</b> Coeff. of linear thermal expansion - Coeff. d'extension thermique lineaire - Linearer Wärmeausdehnungs-Koeffizient Coefficiente de dilatación térmica lineal - <b>Линейное тепловое расширение</b>	°MK (-1)	7,0	metodo disponibile available method - méthode disponible - verfügbare methode - método disponible - <b>используемый метод</b>	UNI EN ISO 10545-8
	<b>Resistenza agli sbalzi termici</b> Thermal shock resistancy - Résistance aux chocs thermiques - Temperaturwechsel beständig keit Resistencia a choque térmico - <b>Стойкость к перепадам температуры</b>	-	resiste resist - résiste widerstandsfähig - resiste <b>стойкий</b>	metodo disponibile available method - méthode disponible - verfügbare methode - método disponible - <b>используемый метод</b>	UNI EN ISO 10545-9
	<b>Resistenza alle macchie</b> Stain resistance - Résistance au tâches Flecken beständigkeit - Resistencia a las manchas <b>Стойкость к образованию пятен</b>	-	≥ 3	3 MIN	UNI EN ISO 10545-14
	<b>Resistenza ai prodotti chimici di uso domestico</b> Resistance to chemical products - Résistance aux produits chimiques Beständigkeit gegen Chemikalien - Resistencia a los productos químicos - <b>Стойкость к бытовым химикатам</b>	-	conforme conform - conforme gleichmässig - conforme <b>соответствует</b>	MIN GB	UNI EN ISO 10545-13
	<b>Resistenza agli acidi e alle basi a bassa concentrazione</b> Resistant to acids and low concentration bases - Résistance aux acides et aux bases à faible concentration - Widerstandsfähig gegenüber niedrig konzentrierten Säuren und Laugen - Resistencia a los ácidos y las bases de baja concentración - <b>Стойкость к низким концентрациям кислот и щелочей</b>	-	MIN GLB	secondo classificazione prodotto according to product classification selon classification produit Gemäß Produktklassifizierung <b>СОГЛАСНО КЛАССИФИКАЦИИ ПРОДУКЦИИ</b>	UNI EN ISO 10545-13
	<b>Resistenza al gelo</b> Frost resistance - Résistance au gel Frostbeständigkeit - Resistencia al hielo <b>Морозостойкость</b>	-	resiste resist - résiste widerstandsfähig - resiste <b>стойкий</b>	richiesta request - demande anfrage - solicitud <b>требуемое значение</b>	UNI EN ISO 10545-12
	<b>Stabilità dei colori</b> Colour stability - Stabilité des coloris - Lichtechtheit der Färbung - Estabilidad de los colores - <b>Цветостойкость</b>	-	stabile stable - stable stabil - estable <b>стойкий</b>	metodo disponibile available method - méthode disponible - verfügbare methode - método disponible - <b>используемый метод</b>	DIN 51094
	<b>E' a disposizione della gentile clientela la lista dei nostri articoli certificati dall'ente UNI</b> The list of our items certified by "UNI" is available for our customers - Pour tous nos clients est disponible la liste de nos produits avec la certification UNI Den Kunden steht eine Aufstellung zur Verfügung, der Artikeln die mit UNI Zertifikat bescheinigt wurden La lista de nuestros artículos certificados por el Instituto UNI está a disposición de la estimada clientela. <b>Мы можем предоставить в распоряжении наших заказчиков перечень нашей продукции, сертифицированной органом UNI</b>				

N° DI CONCESSIONE P0219



**NEMO**  
NEMOTILE.COM

# COTTO CEMENTO



# COTTO CEMENTO



# LOCATIONS

## MANHATTAN SHOWROOM

48 East 21st Street  
New York, NY 10010  
p. 212.505.0009  
f. 212.777.9053

## MANHATTAN CONTRACTOR SHOWROOM

49 East 20th Street  
New York, NY 10003  
p. 212.505.0009  
f. 212.477.1455

## QUEENS SHOWROOM

177-02 Jamaica Avenue  
Jamaica, NY 11432  
p. 718.291.5969  
f. 718.291.5992

## LONG ISLAND SHOWROOM

277 Old Country Rd.  
Hicksville, NY 11802  
p. 516.935.5300  
f. 516.935.5322

## PHILADELPHIA SHOWROOM

1520 Locust Street  
Philadelphia, PA 19102  
p. 215.558.3698  
f. 215.545.2796

## NEW JERSEY SHOWROOM

21 White Street  
Red Bank, NJ 07701  
p. 732.677.1044  
f. 732.352.6961



**NEMO**  
NEMOTILE.COM